

TEST REPORT

NUMBER : DELH20002443

DATE : 25TH FEB, 2020



ORIGINAL SAMPLE



NUMBER : DELH20002443

TEST REPORT

DATE : 25TH FEB, 2020

APPLICANT: TAPRATH ELASTOMERS LLP
GUT NO. 197, NEHROLI VILLAGE WADA ROAD, PALGHAR 421312, MAH - INDIA

ATTN: MR. JENET AJMERA

SAMPLE DESCRIPTION: THE SUBMITTED SAMPLE SAID TO BE – TAPBIO F2610

DATE RECEIVED : 13TH FEB, 2020
BUYER'S NAME : -
BUYING AGENT/ CONTACT : --
ORDER NO. : --
STYLE NO. : FILM
COLOR : TRANSPARENT
END USE : FOOD PACKAGING
SEASON : --
COUNTRY OF DESTINATION : --
MANUFACTURER'S NAME : --

TESTS CONDUCTED: AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).


CONCLUSION:

TESTED SAMPLE	TEST PARAMETER/ STANDARD	RESULT
SUBMITTED SAMPLE	OVERALL MIGRATION (REGULATION (EU) 10/2011 AND IT'S AMENDMENT REGULATION (EU) 2016/1416 ON FOOD CONTACT PLASTICS)	M

NOTE: M = MEET CLIENT'S REQUIREMENT
= NO SPECIFIED REQUIREMENT

F = BELOW CLIENT'S REQUIREMENT
N/A = NOT APPLICABLE

PREPARED & CHECKED BY
for INTERTEK INDIA PVT. LTD



SANJAY SADANA
TECHNICAL MANAGER –HARDLINE



TEST REPORT

1. OVERALL MIGRATION TEST:

(REGULATION (EU) 10/2011 AND its AMENDMENT REGULATION (EU) 2016/1416 ON FOOD CONTACT PLASTICS)
TEST METHOD: EN1186

TEST CONDITIONS AND RESULTS:

SIMULANT USED	TEST TEMPERATURE (°C)	CONTACT DURATION	RESULT IN (mg/dm ²)	MAX. LIMIT (mg/dm ²)
10% ETHANOL	40 °C	10 DAYS	<5.0	10 mg/dm ²
3% ACETIC ACID	40 °C	10 DAYS	<5.0	
95% ETHANOL	40 °C	10 DAYS	<5.0	
ISO – OCTANE	20 °C	02 DAYS	<5.0	

REMARK : <= LESS THAN
RESULTS ARE GIVEN IN mg/dm²=milligram per decimeter square

END OF TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct

