

TEST REPORT

APPLICANT: TAPRATH ELASTOMERS LLP
GUT NO. 197, NEHROLI VILLAGE, WADA ROAD,
WADA, PALGHAR 421312, MAH - INIDA

ATTN: MR. JENET AJMERA

SAMPLE DESCRIPTION: THE SUBMITTED SAMPLE SAID TO BE - TAPBIO F 20 T

DATE RECEIVED : 07TH JAN 2020
BUYER'S NAME : --
BUYING AGENT/ CONTACT : --
ORDER NO. : --
STYLE / ITEM NO : FILM
COLOR : TRANSPARENT
END USE : FOOD PACKAGING
SEASON : --
COUNTRY OF ORIGIN : --
COUNTRY OF DESTINATION : --
MANUFACTURER'S NAME : --

TESTS CONDUCTED: AS REQUESTED BY THE APPLICANT. FOR FURTHER DETAILS, PLEASE REFER TO THE ENCLOSED PAGE (S).

CONCLUSION:

<u>TESTED SAMPLE</u>	<u>STANDARD</u>	<u>RESULT</u>
SUBMITTED SAMPLE	OVERALL MIGRATION (REGULATION (EU) 10/2011 AND IT'S AMENDMENT REGULATION (EU) 2016/1416 ON FOOD CONTACT PLASTICS)	M

NOTE: M = MEET CLIENT'S REQUIREMENT
= NO SPECIFIED REQUIREMENT

F = BELOW CLIENT'S REQUIREMENT
N/A = NOT APPLICABLE

PREPARED & CHECKED BY
for INTERTEK INDIA PVT. LTD

Sanjay Sadana
SANJAY SADANA
TECHNICAL MANAGER -HARDLINE



TEST REPORT

TEST CONDUCTED:

1. OVERALL MIGRATION TEST:
(REGULATION (EU) 10/2011 AND IT'S AMENDMENT REGULATION (EU) 2016/1416 ON FOOD CONTACT PLASTICS)
TEST METHOD: EN1186

TEST CONDITIONS AND RESULTS:

SIMULANT USED	TEST TEMPERATURE (°C)	CONTACT DURATION	RESULT IN (mg/dm ²) (1)	LIMIT (mg/dm ²)
10% ETHANOL	40 °C	10 DAYS	<5.0 mg/dm ²	10 mg/dm ²
95% ETHANOL	40 °C	10 DAYS	<5.0 mg/dm ²	10 mg/dm ²
3% ACETIC ACID	40 °C	10 DAYS	<5.0 mg/dm ²	10 mg/dm ²
ISO OCTANE	20 °C	02 DAYS	<5.0 mg/dm ²	10 mg/dm ²

RESULTS ARE GIVEN IN mg/dm²

TESTED PART:

1. TAPBIO

END OF TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

